

# MARTOL LS 20 I



COLD DRAWING



## Prelubricant to draw painted aluminium

### DESCRIPTION

- Solid lubricants, to apply molten, to prelub aluminium with **polyester or epoxy paint**, with high lubricity and resistance to growing

### SPECIFICATIONS

Hydrocarbon base fulfils all principal Pharmacopoeias: European Pharmacopoeia, F.U., DAB, BP etc.

Additivation is reported in FDA 21 CFR 170.30 regarding «*Eligibility for classification as generally recognize as safe (GRAS)*».

**The product acknowledges the future law concerning aluminium for food container**

### APPLICATION

**MARTOL LS 20 I** is expressly formulated for the following reasons:

- lubricity increase of petroleum base.
- melting point decrease of the base
- cloudiness decrease of the base

All the components are oxidation stable in thin film as well

## Typical Characteristics

Test methods	Determinations	MARTOL LS 20 I
Visual	Aspect	Solid, tacky
Visual	Colour	White, translucent
--	Smell	Without smell
ASTM D-4052	Density at 80°C	0,833
ASTM D-445	Viscosity at 100°C	9,75
ASTM D 97	Pour point	+45